


LOCTITE[®] 5366[™]

November 2004

PRODUCT DESCRIPTION

LOCTITE[®] 5366[™] provides the following product characteristics:

Technology	Silicone
Chemical Type	Acetoxy silicone
Appearance (uncured)	Clear paste
Components	One component - requires no mixing
Cure	Room temperature vulcanizing (RTV)
Application	Bonding or Sealing
Flexibility	Enhances load bearing & shock absorbing characteristics of the bond area.

LOCTITE[®] 5366[™] has been designed specifically for use as a bonding agent to ensure perfect sealing, as well as bonding and protection. Typical applications include sealing side windows in trains, sealing heat sources (ovens, heat exchangers, steam circuits, water heaters), providing protection/insulation of electrical boxes, bonding of HCR silicones and in the general care and maintenance applications in various fields. This product is typically used in applications up to 250 °C.

TYPICAL PROPERTIES OF UNCURED MATERIAL


Specific Gravity @ 25 °C	1.04
Extrusion Rate, g/min	100
Flow, ISO 7390, mm	<2
Flash Point - See MSDS	

TYPICAL CURING PERFORMANCE
Surface Cure

LOCTITE[®] 5366[™] becomes tack free on exposure to atmospheric moisture within 5 minutes at 23±2°C / 50±5%RH.

Depth of Cure

The graph below shows the increase in depth of cure with time at 23±2°C / 50±5% RH.


TYPICAL PROPERTIES OF CURED MATERIAL

After 7 days @ 25 °C / 50% RH, 5 mm thick film

Physical Properties:

Shore Hardness, ASTM D 2240, Durometer A	25
Elongation, at break, ASTM D 412, %	530
Tensile Strength, ASTM D 412	N/mm ² 2.5 (psi) (360)

Electrical Properties:

Dielectric Breakdown Strength, ASTM D 149, kV/mm	18
Volume Resistivity, IEC 60093, Ω·cm	1×10 ¹⁴
Dielectric Constant, IEC 60250: 1MHz	2.8

TYPICAL PERFORMANCE OF CURED MATERIAL
Adhesive Properties

Cured for 7 days @ 25 °C / 50% RH

Lap Shear Strength, ISO 4587:

Aluminum(1 mm sand-blasted thick bondline)	N/mm ² 2 (psi) (290)
--	------------------------------------

TYPICAL ENVIRONMENTAL RESISTANCE
Typical Fluid Immersion Properties

Aged @ 22°C for 5,000 hours, 2 mm thick film:

Sodium Carbonate, 25%:	
Volume Swell, %	-0.2
Change in Tensile Strength, %	-12
Change in Elongation, %	-10
Sodium Chloride, 25%:	
Volume Swell, %	-0.1
Change in Tensile Strength, %	0
Change in Elongation, %	0
Hydrochloric Acid, 2%:	
Volume Swell, %	-0.1
Change in Tensile Strength, %	-8
Change in Elongation, %	-8
Lactic Acid, 12%:	
Volume Swell, %	0.3
Change in Tensile Strength, %	4
Change in Elongation, %	10
Citric Acid, 12%:	
Volume Swell, %	-0.1
Change in Tensile Strength, %	-0.3
Change in Elongation, %	0
Soda, 25%:	
Volume Swell, %	-7
Change in Tensile Strength, %	-15
Change in Elongation, %	-15
Bleach, commercial concentration:	
Volume Swell, %	-1
Change in Tensile Strength, %	-20
Change in Elongation, %	-15

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Directions for use

1. For best performance bond surfaces should be clean and free from grease.
2. Moisture curing begins immediately after the product is exposed to the atmosphere, therefore parts to be assembled should be mated within a few minutes after the product is dispensed.
3. When joint is assembled pressure should be applied to spread the adhesive out and fill the joint completely.
4. The bond should be allowed to cure (e.g. seven days), before subjecting to heavy service loads.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental**

damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1